

## 51789

Peel ply

Ideally suited to aerospace applications

### Features and Benefits

- Lightweight nylon 6.6 which has been heat set and scoured for use directly against laminates or bond lines.
- Imparts a very fine weave pattern upon removal from the laminate.
- Available coated and non-coated, depending on user requirement.
- Approved on a range of OEM specifications for composite manufacture and metal bonding.
- Solvay does not recommend for use with phenolic resin systems or prepreg as acid in the catalyst can break down nylon materials. Customers are advised to carry out their own internal compatibility tests.
- Manufactured by Precision Fabrics Group (PFG).

### PRODUCT VARIANTS

- NAT – Scoured and heat set finish
- IO – International Orange for easy identification
- VLP – Very Low Porosity finish
- SRB – Super Release Blue (inert, heat stabilised, cross-linked polymer finish)
- GFR – Cross-linked, low transfer fluorocarbon finish for ease of release

### PROPERTIES

Maximum use temperature	232°C	450°F
Color	White, blue, orange and yellow	
Fabric type	Nylon	
Fabric weight	62.7g/m <sup>2</sup>	1.85oz/yd <sup>2</sup>

### AVAILABILITY

Standard width	1.47m	58in
Standard length	274.3m	300yd
	Slit widths available	

## STORAGE

No special storage conditions required.

## HEALTH & SAFETY

Please refer to the product MSDS for safe handling, personal protective equipment recommendations and disposal considerations.

DISCLAIMER: The data and information provided in this document have been obtained from carefully controlled samples and are considered to be representative of the product described. Solvay does not express or imply any guarantee or warranty of any kind including, but not limited to, the accuracy, the completeness or the relevance of the data and information set out herein. Because the properties of this product can be significantly affected by the fabrication and testing techniques employed, and since Solvay does not control the conditions under which its products are tested and used, Solvay cannot guarantee the properties provided will be obtained with other processes and equipment. No guarantee or warranty is provided if the product is adapted for a specific use or purpose. Solvay declines any liability with respect to the use made by any third party of the data and information contained herein. Solvay has the right to change any data or information when deemed appropriate. All trademarks are the property of their respective owners. ©2017, Solvay. All rights reserved.

---

### Solvay

Composite Materials HQ  
4500 McGinnis Ferry Rd  
Alpharetta, GA 30005-3914 USA

21 March 2013

