

60001

Peel ply

Ideally suited to aerospace applications

Features and Benefits

- Porous, polyester peel ply.
- Heat set and scoured, for use directly against laminates or bond lines.
- Available coated and non-coated, depending on user requirement.
- Approved on a range of OEM specifications for composite manufacture and metal bonding.
- This product is particularly recommended for use with phenolic resin systems.
- Also recommended for composite manufacture and metal bonding applications.
- Manufactured by Precision Fabrics Group (PFG).

PRODUCT VARIANTS

- NAT – Scoured and heat set finish
- IO – International Orange for easy identification
- VLP – Very Low Porosity finish
- SRB – Super Release Blue (inert, heat stabilised, cross-linked polymer finish)

PROPERTIES

Maximum use temperature	204°C	400°F
Color	Natural, blue and orange	
Fabric type	Polyester	
Fabric weight	85g/m ²	2.5oz/yd ²

AVAILABILITY

Standard width	1.52m	60in
Standard length	274m	300yd
	Slit widths available	

STORAGE

No special storage conditions required.

HEALTH & SAFETY

Please refer to the product MSDS for safe handling, personal protective equipment recommendations and disposal considerations.

DISCLAIMER: The data and information provided in this document have been obtained from carefully controlled samples and are considered to be representative of the product described. Solvay does not express or imply any guarantee or warranty of any kind including, but not limited to, the accuracy, the completeness or the relevance of the data and information set out herein. Because the properties of this product can be significantly affected by the fabrication and testing techniques employed, and since Solvay does not control the conditions under which its products are tested and used, Solvay cannot guarantee the properties provided will be obtained with other processes and equipment. No guarantee or warranty is provided if the product is adapted for a specific use or purpose. Solvay declines any liability with respect to the use made by any third party of the data and information contained herein. Solvay has the right to change any data or information when deemed appropriate. All trademarks are the property of their respective owners. ©2017, Solvay. All rights reserved.

Solvay

Composite Materials HQ
4500 McGinnis Ferry Rd
Alpharetta, GA 30005-3914 USA

21 March 2013



SOLVAY

asking more from chemistry®